



Jenolite Red Oxide Primer - HB48

Technical Data Sheet

Description

An Alkyd based, quick drying primer offering outstanding adhesion, moisture resistance and corrosion protection due to incorporation of modified Zinc Phosphate.

Designed for airless or conventional application for structural steelwork, chassis, steel fabrication etc. It is easy to apply without fear of runs or sags at high wet film thickness.

Technical Data

Coverage	8-10 sq.m per litre @ 50 microns dry film thickness
Flashpoint	25°C
Colour	Red Oxide
Maximum VOC	< 0.45 kg/L

Cleaning

Ensure surfaces to be coated are dry and must be cleaned using the appropriate solvent to remove all traces of contaminants.

Storage

Store between 5°C - 25°C. When not in use, cans must be kept sealed.

Shelf Life

12 months from delivery date in original sealed containers.

Health and Safety

Refer to MSDS and tin label prior to use.
Suitable respiratory equipment should be worn when spraying.

The information contained in this document is given in good faith and is based on results gained from experience and tests. However all recommendations and suggestions are made without guarantee since the conditions of use are beyond our control. Goods are supplied subject to the terms and conditions of sale, a copy of which is available on request.

ISSUE No: 1

ISSUE DATE: April 2015

ISSUED BY: CH